

What is claimed is:

1. A fused silica soot production furnace comprising:
 a precursor delivery system for delivering silicon containing precursor to the furnace;
 a burner for producing a flame and converting the precursor into a silica-containing soot; and
 a crown constructed from a foamed refractory material having a network of interconnected pores.
2. The furnace of claim 1, wherein the pores in the foamed refractory material have a surface area greater than $0.5 \text{ m}^2/\text{g}$.
3. The furnace of claim 2, wherein foamed refractory material has a porosity greater than 50%.
4. The furnace of claim 2, wherein the foamed refractory has a density less than 1.5 g/cm^3 .
5. The furnace of claim 2, wherein the foamed refractory contains iron and sodium impurities less than 10 parts per million.
6. A method of manufacturing a fused silica boule comprising the steps of:
 providing a furnace including crown constructed from a foamed refractory material having a network of interconnected pores; and
 introducing a silicon-containing precursor into a flame to produce fused silica particles, collecting the particles on a collection surface and consolidating the particles on the collection surface to form a boule.
7. The method of claim 6, wherein the pores in the foamed refractory material have a surface area greater than $0.5 \text{ m}^2/\text{g}$.

10034533 122401

8. The method of claim 7, wherein foamed refractory material has a porosity greater than 50%.
9. The method of claim 7, wherein the foamed refractory has a density less than 1.5 g/cm³.
10. The method of claim 7, wherein the foamed refractory contains iron and sodium impurities less than about 10 parts per million.

10034539 122104
T0222 8854001